

Report No.: 304147982c 001
Client: ALLFLASH PRODUKTIONS + VERTRIEBS GMBH
Contact Information: Lettenbachstr., Tussenhausen, Bavaria, Germany

Sample Description as Declared:

No. Of Sample : Four(4)
Colour : Fluorescent yellow, Fluorescent orange-red
Style No. : AL-1206, AL-1208, AL-1209, AL-1215, AL-1306, AL-1307, AL-1315, AL-1316
Style Name# : Kids Safety wests
Standard : EN 17353:2020 Protective clothing - Enhanced visibility equipment for medium risk situations - Test methods and requirements
Remark : Retest of 304147982b 001

Applicant's Provided Care Instruction/Label:



MAX 25X

Sample obtaining method: Sending by customer
Condition at delivery: Test item complete and undamaged.
Sample Receiving date: 2025-12-15
Testing Period: 2025-12-15 to 2025-12-18
Place of testing: Textiles laboratory Suzhou

For and on behalf of
TÜV Rheinland (Suzhou) Co., Ltd.

2025-12-19

Carmen Yan / Department Manager

Date

Name / Position

*Sample information is provided by customer. Test result is drawn according to the kind and extent of tests performed.
This test report relates to the above mentioned test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.
"Decision Rule" document announced in our website (<https://www.tuv.com/landingpage/en/qm-gcn/>) describes the statement of conformity and its rule of enforcement for test results are applicable throughout this test report.*

Test Report No.: 304147982c 001

Page 2 of 4

Summary of Test Result(s):

Test parameter	Result	Failed Material No.
Appearance Change After Washing	Pass	-

Material List:

Material No.	Material	Color	Location
M001	Whole Product	Fluorescent yellow	Kids safety vest, 100% polyester
M002	Whole Product	Fluorescent yellow	Kids safety vest, 100% recycle polyester

Test Report No.: 304147982c 001 Page 3 of 4

1. Appearance Change After Washing

Test method : EN ISO 6330:2021
 Apparatus : Front-loading horizontal rotating drum type
 Test condition : Washing programme 4N, at 40°C, with 20g Non-phosphate detergent 3, 2kg loading, line dry

M001 **Requirement**

After twenty - five washes

Colour change 4

Cross staining 4-5

Observation Some print lost was found on the silver reflective tape.
Slight loose ends were found along the edge of the care label.
The ends of the piping raveled slightly.

Conclusion The general appearance of the washed sample was satisfactory. Satisfactory

M002 **Requirement**

After twenty - five washes

Colour change 4

Cross staining 4-5

Observation Some print lost was found on the silver reflective tape.
Slight loose ends were found along the edge of the care label.
The ends of the piping raveled slightly.

Conclusion The general appearance of the washed sample was satisfactory. Satisfactory

Test Report No.: 304147982c 001

Page 4 of 4

Sample Photos



- END -

